

### Ballistic Glass Specifications: All Glass Laminates

Product	Average Thickness	Weight/Sq.Ft.	Testing	Threat
PAS 001AG	1.185"	14.91 lbs.	PAS Range	3-Shots 9mm
PAS 002AG	1.40"	17.45 lbs.	PAS Range	3-Shots .357 mag 9mm
PAS 003AG	1.59"	19.91 lbs.	PAS Range	3-Shots .44 mag .357 mag 9mm
PAS 004AG	1.99	24.91 lbs.	PAS Range	3-Shots 308 30-06 30 cal M-1 7.62 x 39 SC AK-47 5.56 m 193
PAS 008AG	2.40"	29.91 lbs.	PAS Range	1-Shot 30-06 AP M2

### Ballistic Glass Specifications: Glass/Clad Laminates

Product	Average Thickness* #	Weight/Sq.Ft.	Testing	Threat
PAS 002	.825"	8.98 lbs.	PAS Range	3-Shots .357 9mm .44 SWC
PAS 003	.950"	11.11 lbs.	PAS Range	3-Shots .44 FMJ 7.62 x 25 SJ Tokarev
PAS 004	1.075"	11.89 lbs.	PAS Range	3-Shots .357 KTW 30 cal M-1 .44 FMI  2-Shots 7.62 x 39 SC AK-47  1-Shot

				30-06 308 Win.
PAS 005	1.350"	14.67 lbs.	PAS Range	1-Shot 30 cal M-1 30-06 7.62 x 51 (308)  3-Shots AK-47 5.56 x 45 (223) HP White 7.62 x 39 (123) SC
PAS 005MH	1.475"	17 lbs.	PAS Range	3-Shots 7.62 Nato 30 Cal. M-1 30-06 AK-47
PAS 008AP	2.27"	26.71 lbs.	PAS Range	1 Shot 7.62 AP

\*Add .337" when bonding to OEM glass.  
#Add .237" when ordering Low Spall units.

#### UL Listed Laminates

Product	Average Thickness*	Weight/Sq.Ft.	Testing	Threat
PAS-BR-2	.993"	10.72 lbs.	UL Listed	3-Shots .357
PAS-BR-3	1.39"	15.64 lbs.	UL Listed	3-Shots .44 mag
PAS-BR-4	1.45"	15.45 lbs.	UL Listed	3-Shots 30-06
PAS-BR-6	1.15"	13.06 lbs.	UL Listed	5-Shots 9 MM
PAS-BR-8	2.32"	25.59 lbs.	UL Listed	5-Shots 7.62 FMJ M-Ball 30-06 AP

\*Add .337" when bonding to OEM glass.

